



MOHM CHEMICAL SDN. BHD. (Co. No. 276851-U)

MCX MARKETING SDN. BHD. (Co. No. 363532-T)

H.Q. : No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor, Malaysia.
Tel: (60) 7 333 1222 Fax: (60) 7 332 0545/ 333 7919

Branch: No. 43, Jalan Tambur 33/19, Sek. 33, Shah Alam Technology Park,
40400 Shah Alam, Selangor, Malaysia.

Tel: (60) 3 5124 0876/ 5124 0878 Fax: (60) 3 5124 0877

Email: info@mochem.com Website: www.mochem.com/ www.xtraseal.com

TECHNICAL DATA SHEET

x'traseal® B-168 BUTYL SEALANT

DESCRIPTION:

x'traseal® B-168 IS A ONE PART SEALER MAINLY CONSISTS BUTYL RUBBER AND SYNTHETIC RESIN. BECAUSE OF RELATIVELY LOW COST, EASY WORKABILITY, MINOR CLEAN UP PROBLEM, ELASTIC COMPOUNDS WITH PERMANENT FLEXIBILITY AND GOOD WEATHER PROPERTIES, IT IS MOST SUITABLE FOR WATER-PROOFING, DUST-PROOFING AND HERMETICALLY SEALING OF CONTAINERS, AUTOMOBILES, BUILDINGS AND VARIOUS APPLIANCES.

FEATURES:

- ◆ LOW COST
- ◆ OUTSTANDING DURABILITY.
- ◆ ONE PARTS NO MIXING.
- ◆ GOOD ADHESION AND EXCELLENT ELASTICITY TO METALS, WOODS, PLASTICS, GLASS AND MANY OTHER ENGINEERING MATERIALS.
- ◆ 100% WEATHER PROOF.
- ◆ USE WITHOUT PRIMER.
- ◆ EXCELLENT GUNNABILITY.
- ◆ VERY STABLE PROPERTIES IN A COMPOSITE CONTAINER.

USES:

- ◆ FOR JOINTS OF CONTAINERS.
- ◆ FOR JOINTS OF AUTOMOBILES, BUS AND OTHER VEHICLES.
- ◆ SEALING OF JOINTS BETWEEN WINDOW SASH AND WALL.
- ◆ SEALING OF JOINTS IN ZINC ROOFS AND SLATE ROOFS.

LIMITATIONS:

B-168 IS NOT SUITABLE FOR HIGH JOINT MOVEMENT SUBSTRATE.

COLOUR:

GREY. OTHER COLOUR CAN BE MANUFACTURED ON REQUEST.

APPLICATION:

- ◆ SURFACE MUST BE CLEAN AND DRY.
- ◆ CUT NOZZLE TO DESIRED SIZE.
- ◆ INSERT CARTRIDGE INTO CAULKING GUN.
- ◆ PUSH SEALANT AHEAD FOR UNIFORM BEAD.
- ◆ TOOL WITHIN 5 MINUTES.
- ◆ CLEAN OFF EXCESS SEALANT WITH MINERAL SPIRIT.



MOHM CHEMICAL SDN. BHD. (Co. No. 276851-U)

MCX MARKETING SDN. BHD. (Co. No. 363532-T)

H.Q. : No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor, Malaysia.
Tel: (60) 7 333 1222 Fax: (60) 7 332 0545/ 333 7919

Branch: No. 43, Jalan Tambur 33/19, Sek. 33, Shah Alam Technology Park,
40400 Shah Alam, Selangor, Malaysia.

Tel: (60) 3 5124 0876/ 5124 0878 Fax: (60) 3 5124 0877

Email: info@mochem.com Website: www.mochem.com/ www.xtraseal.com

TECHNICAL DATA SHEET

x'traseal® B-168 BUTYL SEALANT

SPECIFICATION:

BASE	BUTYL RUBBER
APPEARANCE	NON-SAGGING PASTE
SOLVENT	ORGANIC SOLVENT
SPECIFIC GRAVITY	1.15±0.10
SOLID CONTENTS	85±5%
SHORE A HARDNESS	25 APPROX.
SLUMP	NONE
ELONGATION	350%
TACK FREE TIME	60 MINUTES
CURE THROUGH TIME	NONE CURING SYSTEM
EXTRUDABILITY	2.2 g/s MINIMUM
STAIN	NONE
WEATHER PROOF	EXCELLENT
APPLICATION TEMP.	-10°C TO 50°C
SERVICE TEMP.	-50°C TO 100°C
SHELF LIFE	12 MONTHS

CAUTION:

HIGHLY FLAMMABLE!

UNCURED SEALANT MAY CAUSE SKIN, EYE AND RESPIRATORY SYSTEM IRRITATION.
USE ONLY IN WELL VENTILATED AREAS.

USE APPROPRIATE PERSONAL PROTECTION TO AVOID CONTACT WITH SKIN AND EYES.

IN CASE OF EYE CONTACT OR IRRITATION, FLUSH EYE IMMEDIATELY WITH RUNNING WATER FOR 15 MINUTES AND GET MEDICAL ATTENTION.

IN CASE OF SKIN CONTACT, WASH AFFECTED AREAS WITH HAND CLEANER FOLLOWED BY SOAP AND WATER.

FOR FURTHER HEALTH AND SAFETY INFORMATION CONSULT THE CURRENT MATERIAL SAFETY DATA SHEET.